## We claim:

10

30

- A molding composition made from a high-molecular-weight propylene polymer with a melt
  mass-flow rate MFR of from 0.3 to 1 g/10 min, to ISO 1133 at 230°C and 5 kg, and with a proportion in the range from 2 to 20% by weight of β modification crystallites.
  - 2. A molding composition as claimed in claim 1, where the proportion of  $\beta$  modification crystallites is in the range from 2 to 10% by weight, in particular from 4 to 8% by weight.
  - 3. A molding composition as claimed in claim 1 or 2, where a high-molecular-weight propylene homopolymer is used.
- 4. A molding composition as claimed in claim 1 or 2, where a high-molecular-weight propylene copolymer is used and has up to 30% by weight of other copolymerized olefins having up to 10 carbon atoms.
- 5. A molding composition as claimed in any of the preceding claims, where the high-molecular-weight propylene polymer has a melt mass-flow rate MFR of from 0.75 to 0.9 g/10 min.
  - 6. A molding composition as claimed in any of the preceding claims, where the DSC crystallization onset to ISO 11357-1 is at a temperature above 122°C.
- A molding composition as claimed in claim 6, where the DSC crystallization onset to
  ISO 11357-1 is at a temperature of from 123 to 127°C.
  - 8. A molding composition as claimed in any of the preceding claims, which comprises from 0.001 to 0.5% by weight of a quinacridone pigment as nucleating agent.
  - 9. A molding composition as claimed in claim 7, where the gamma phase of linear transquinacridone is used as nucleating agent.
- 10. A process for preparing molding compositions as claimed in claim 8 or 9 by mixing the high-35 molecular-weight propylene polymer with the nucleating agent, where the mixing takes place in a mixing apparatus at temperatures of from 180 to 320°C.
  - 11. A process as claimed in claim 10, wherein the mixing takes place in an extruder.
- 40 12. The use of the molding compositions as claimed in any of claims 1 to 9 as films, fibers, or

moldings.

- 13. The use of the molding compositions as claimed in any of claims 1 to 9 as materials for pipes.
  - 14. A pipe obtained from the molding compositions as claimed in any of claims 1 to 9.